

CEREALI/AL/B - N



IT IMPIEGO

Tubo in gomma cord per mandata di prodotti alimentari liquidi e solidi ad alto potere abrasivo quali zuccheri, grano, cereali e sfarinati per alimentazione. È particolarmente idoneo per granuli di pvc.

Conforme agli Standard FDA.

- **TEMPERATURA:** -30°C +80°C

STRUTTURA

- **Sottostrato:** liscio in gomma bianca alimentare altamente resistente all'abrasione.
- **Rinforzi:** sintetici ad alta resistenza e cordicella di rame.
- **Copertura:** in gomma blu resistente all'abrasione, agli agenti atmosferici e all'ozono.
- **Superficie:** liscia ad impressione tela.
- **Marchatura:** listino scritto bianco e blu "H.T. - FOOD QUALITY - F.D.A."

EN APPLICATION

Softwall rubber hose suitable for delivery of solids and bulk liquids food products as sugar, corn, flavour and pvc granules.

According to FDA Standards.

- **TEMPERATURE RANGE:** -30°C +80°C

CONSTRUCTION

- **Tube:** white, smooth abrasion, food quality resistant rubber.
- **Reinforcement:** high strength synthetic textile plies and copper wire.
- **Cover:** blue, abrasion and weathering resistant rubber.
- **Surface:** smooth fabric finished.
- **Branding:** white blue writing list "H.T. - FOOD QUALITY - F.D.A."

DIAMETRO INTERNO INSIDE DIAMETER		DIAMETRO ESTERNO OUTSIDE DIAMETER		PESO TEORICO WEIGHT		PRESS. ESERCIZIO WORKING PRESSURE		PRESS. SCOPPIO BURST PRESSURE		LUNGHEZZA LENGTH	
mm	inch	mm	inch	kg/mt	lbs/ft	bar	psi	bar	psi	mt	ft
CEREALI/AL/B											
102	4"	112	4.3/8"	2.00	1.35	5	75	15	225	20	65.5
102	4"	118	4.5/8"	3.10	2.08	5	75	15	225	20	65.5
CEREALI/AL/N											
80	3.5/32"	92	3.9/32"	2.60	1.75	5	75	15	225	40	131

Altri diametri e/o pressioni realizzabili su richiesta - Le caratteristiche e i dati tecnici possono essere modificati senza preavviso.

Other diameters and/or pressures are feasible upon request - The characteristics and technical data could be changed without warning.